

Method for making non-clinker cement by wet-milling flyash and product thereof

Patent number: CN1105344
Publication date: 1995-07-19
Inventor: JIESHENG GAO (CN); QINGLIN DU (CN)
Applicant: LIANYUNGANG CITY INST OF BUILD (CN)
Classification:
- **international:** **C04B7/52; C04B7/00;** (IPC1-7): C04B7/28; C04B18/06; C04B28/18
- **european:** C04B7/52
Application number: CN19940111221 19940113
Priority number(s): CN19940111221 19940113

Report a data error here

Abstract of **CN1105344**

The non-clinker cement is made up from wet flyash discharged from steam-power plant, lime and gypsum through separately grinding and mixing. This low-grade (No.275) cement may be used to produce non-burning brick or building block, mortar and concrete No.13, or to mix with ordinary Port/and cement.

Data supplied from the **esp@cenet** database - Worldwide